Nanomaterial Mechanics Explorer (nanomatmech): Dislocation dynamics

Michael Sakano†, Mitch Wood‡, David Johnson‡, Alejandro Strachan‡

† Department of Applied Sciences-Biomedical Engineering, University of North Carolina at Chapel Hill

‡ School of Materials Engineering, Purdue University

Background

- Dislocations, or atomic linear defects in crystal structures, dictate much of the mechanical response of materials
- No current predictive dislocation analysis tool on the nanoHUB
- Simulation tools such as Molecular dynamics solve for the movement of atoms, and in turn the dislocations



(Left) BCC crystal (Fe)[1]

(Right) FCC crystal (Cu)



Edge Dislocation[2]

Screw Dislocation[2]

Graphical User Interface(GUI)

- Our objective aims to create a GUI to enable wide spread use of simulation tools to predict the behavior of defects in metals



Simulation results of edge dislocation movement

https://nanohub.org/tools/nanomatmech

Initial state of the simulation

Dislocation Core



Final state of the simulation where the applied shear moves the dislocation. Defects are created and simulated using the LAMMPS[4] simulation package.

Characterizing Defects using MD

Dislocation Motion (Resolved Shear Stress) vs. *Dislocation Nucleation (No Resolved Shear Stress)*



Edge Dislocation FCC Copper[3] – Oscillation around 0 GPa conveys gliding motion



Fixed Strain Rate and Temperature[3] – Different magnitudes because dislocations in Copper are partials compared to Iron. Inset shows an example nucleation event at high strain



Edge Dislocation BCC Iron[3] – Increasing stress implies single dislocation takes more stress to move than two partials in a FCC crystal



Double Strain Rate[3] – Yielding occurs at lower strain, material acts more brittle



Edge Velocities[3] – Dislocation cores move at roughly constant value for constant shear rate



Reduced Temperature[3] – Yielding occurs at much later strain, BCC material acts more brittle

Discussion

- Dislocation type depends on relative orientation of: Burgers vector (direction of atom shift), dislocation line and slip plane (closed packed)
- Dot product of the applied shear stress aligns with the slip plane is known as resolved stress (i.e. what moves the dislocation)



FCC Edge Dislocation



FCC Screw Dislocation

Conclusion

- Dislocation behavior dependent on crystal and orientation
- Shear stress causes dislocations to glide or nucleate
- Replicates the behavior of bulk material by modeling at the nanoscale
- GUI presents the topic in a user-friendly manner
- Advanced users can freely create and define their own simulation parameters

Future Work

- More materials/crystal structures
- Greater input flexibility
- Uncertainty Quantification (UQ)
- Upload user data and input files

References

[1] Callister, William D. *Material Science and Engineering An Introduction.* York: Quebecor Versailles, 2007. Print.
[2] Ovito A. Stukowski, Modelling Simul. Mater. Sci. Eng. 18, 015012 (2010)
[3] Rappture.org
[4] LAMMPS software package (lammps.sandia.gov)

This work is funded by the National Science Foundation, Network for Computational Nanotechnology Cyberplatform, Award EEC-1227110. Any opinions, findings, conclusions or recommendations expressed in this material are those of the authors and do not necessarily reflect the views of the National Science Foundation.